



ASA Adhesive Specialities Ltd

Tickitape House, Bone Lane Industrial Estate, Newbury, Berks RG14 5SH
Tel: +44 (0)1635 49825 Fax: +44 (0)1635 45768

N° 6 Rev. 1 First issue 29/03/00 Updated 09/07/02

Product PP hot melt printed 30 my

Ref. 030/03
1

Backing Bi-oriented polypropylene film 28 µm thickness

Adhesive Hot melt

Solvent free adhesive composed by thermoplastic rubber, hydrocarbon resins, plastifiers and antioxidations agents.

Print Ref.030: undersurface positive print up to 6 colours on brown, white, clear
Ref.031: undersurface negative print or float coated print

Characteristic	Tolerances
Backing thickness (µm)	28 ± 3%
Tensile strength (kg/cm)	> 4.7
Elongation (%)	< 165
Quantity of adhesive (g/m ²)	18 ± 2
Total thickness (µm)	46 ± 3
Adhesion to steel (g/cm)	> 400

Application Suitable to close carton-boxes with high adhesion purposes for use either with hand dispenser or with cartonsealing machines. High and low temperatures resistance.

Notice For optimum performance the stock should be rotated and used within 12 months. Where possible the goods should be stored at room temperature, between 14°C and 28°C. Damp storage conditions should be avoided. The self adhesive tapes are pressure sensitive and must be properly applied to guarantee their good performance when sealing boxes.

Prepared QSA

Approved DRS



Certificate Number: 837/1

Registered in London No. 957040

Registered Office: 31 Bone Lane Industrial Estate, Newbury, Berks RG14 5SH

Newbury: Export/Production:
Tel: +44 (0)1635 49825
Fax: +44 (0)1635 45768

Email: info@tickitape.co.uk
Internet: http://www.tickitape.co.uk

Warrington Sales:
Tel: +44 (0)1925 221121
Fax: +44 (0)1925 220536

Z04-40114QH